AMENDMENTS TO THE CLAIMS

Please amend the claims without prejudice, without admission, without surrender of subject matter, and without any intention of creating any estoppel as to equivalents, as follows.

In the Claims:

Claim 1 (currently amended)

1. A radiation-curable abhesive coating composition for coating a web material comprising at least one radiation-curable organopolysiloxane having (meth)acrylic ester groups and at least one photoinitiator, wherein at least one of the photoinitiator(s) is a compound of the general formula (I)



(I)

in which

R^1 is a linear or branched alkyl radical having 4 to 18 carbon atoms,

R^2 is H or an alkyl radical having 1 to 4 carbon atoms,

R^3, R^4 are H or alkyl radicals, which may also have been linked to form a 5- or 6-membered carbon ring, and

R^5 is H or an alkyl or alkanoyl radical.

Claim 2 (cancelled)

Claim 3 (previously presented)

3. The radiation-curable coating composition according to claim 1, wherein at least one of the photoinitiator(s) is a compound of the compound general formula (I) wherein R^1 is a linear or branched alkyl radical having 4 to 12 carbon atoms.

Claim 4 (previously presented)

4. The radiation-curable coating composition according to claim 3, wherein at least one of the photoiniator(s) is a compound of the general formula (I) wherein R^2, $R^5 = H$.

Claim 5 (previously presented)

5. The radiation-curable coating composition according to claim 3, wherein at least one of the photoinitiator(s) is a compound of the general formula (I) in which R^3, $R^4 = CH_3$.

Claim 6 (previously presented)

6. The radiation-curable coating composition according to claim 3, wherein at least one of the photoinitiator(s) of the general formula (I) is present in amounts of from about 0.01 to about 10% by weight, based on the weight of the acrylate-functional silicone component.

Claim 7 (previously presented)

7. The radiation-curable coating composition according to claim 3, which comprise a second photoinitiator not of the general formula (I), wherein the two photoinitiators are present in amounts of from about 0.1 to about 5% by weight, based on the weight of the acrylate-functional silicone compositions.

Claim 8 (previously presented)

8. The radiation-curable coating composition according to claim 3, which further comprises a photosensitizer.

Claim 9 (previously presented)

9. The radiation-curable coating composition according to claim 7, which comprises a photosensitizer.

Claim 10 (previously presented)

10. The radiation-curable coating composition according to claim 3, which further comprises stabilizers, fillers, pigments, other conventional acrylate systems, or further, customary additives.

Claim 11 (previously presented)

11. An abhesive coating which comprises an abhesive and a radiation-curable coating composition according to claim 3.

Claim 12 (previously presented)

12. A web material which is at least partially coated with an abhesive coating obtained by curing a radiation curable coating composition according to claim 3.

Claim 13 (previously presented)

13. The web material according to claim 12, which is a self-adhesive label.

Claim 14 (previously presented)

14. The web material according to claim 12, which is made of plastic, metal or paper.

Claims 15-18 (cancelled)